

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 072 632 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
31.01.2001 Bulletin 2001/05

(51) Int. Cl.<sup>7</sup>: **C08J 5/18**, **C08L 67/02**,  
**C08G 63/183**

(21) Application number: **00306214.8**

(22) Date of filing: **21.07.2000**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU**  
**MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **27.07.1999 KR 9930554**  
**08.10.1999 KR 9943482**

(71) Applicant: **SKC Co., Ltd.**  
**Suwon-city, Kyungki-do (KR)**

(72) Inventors:  
• **Kim, Nam-il**  
**Jangan-gu Suwon City, Kyungki-do (KR)**  
• **Kim, Sang-il**  
**Kwonsun-gu Suwon-City, Kyungki-do (KR)**

(74) Representative: **Kyle, Diana**  
**Elkington and Fife**  
**Prospect House**  
**8 Pembroke Road**  
**Sevenoaks, Kent TN13 1XR (GB)**

(54) **Heat-shrinkable polyester film and method for manufacturing the same**

(57) A heat-shrinkable polyester film including: a repeating unit of trimethyleneterephthalate of 5 - 30% by mole; a repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate of 5 - 30% by mole of the total composition; and a repeating unit of ethyleneterephthalate for the balance. The heat-shrinkable polyester film has excellent printability, mechanical properties, film-and-flux adhesiveness and shrinkage properties, and ease of drawing process. Thus, the heat-shrinkable polyester film can be used as labels or coverings for a variety of containers.

**EP 1 072 632 A2**

## Description

**[0001]** The present invention relates to a heat-shrinkable polyester film, and more particularly, to a heat-shrinkable polyester film used for labels or coverings of containers and a method for manufacturing the same, the heat-shrinkable polyester film having superior transparency, superior printing and mechanical properties, superior film-to-flux adhesiveness, optimum shrinking properties and easy of drawing process.

**[0002]** Heat-shrinkable films have been extensively used for various purposes, for example, for labeling plastic or glass bottles, batteries, or electrolytic condensers, for covering containers, and for fastening or batch-packing stationary or a plurality of containers. Such heat-shrinkable films are mainly formed of polyvinyl chloride, polystyrene and the like. Recently, use of polyester films as such a heat-shrinkable film is increasing.

**[0003]** Requirements for heat-shrinkable films to be used as wrapping or labeling materials, include a good sealing property and an excellent shrinking property, as well as basic film properties such as heat resistance, chemical resistance, weather resistance and good printability.

**[0004]** Conventional heat-shrinkable films formed of polyvinyl chloride or polystyrene are unsatisfactory in terms of heat resistance, chemical resistance, weather resistance and heat-shrinking properties. In particular, polyvinyl chloride based heat-shrinkable films, which contain chlorine components, have been considered to be unfavorable in terms of an environmental aspect because they produce pollutants during incineration. On the other hand, polyethylene films show inferior printability and thus a special purpose ink, rather than common inks, is needed for application to such films. In addition, its high spontaneous shrinkage ratio make it difficult to be stored for a period of time, and causes failure in a printing process.

**[0005]** Meanwhile, more common heat-shrinkable polyester films formed of polyethylene terephthalate (PET) have a satisfactory heat resistance, chemical resistance, weather stability and shrinking property. However, because shrinkage stress and shrinkage ratio are so high, directly labeling or completely covering a container with a heat-shrinkable polyester film causes various problems. In other words, if the shrinkage ratio of the heat-shrinkable polyester film is too high, nonuniform shrinking results due to the deviation of temperature within a shrinkage tunnel or at the surface of the container. As a result, an image printed on the film is distorted, thereby lowering the commercial usefulness of the product.

**[0006]** Recently, for the purpose of saving storage space, use of rectangular containers is increasing. As shown in FIG. 1, when a conventional polyester heat-shrinkable film is used as a label 11 for such a rectangular container 10, shrinkage stress and shrinkage ratio are high in a direction perpendicular to the major shrinkage direction. Due to a difference in the shrinkage ratio at the edges of the rectangular container 10 and at the flat sides of rectangular container 10, after labeling with a polyester heat-shrinkable film, an edge bowing phenomenon 12 occurs at the edge of the label 11, thereby distorting an image printed on the label 11, giving it a poor appearance.

**[0007]** On the other hand, as for a film to be used as a small label, a shrinkage ratio of 30% or more in 80°C-water is high enough. As for a film to be used to fully cover a bottle, for example, a beer bottle which must be kept at low temperatures to prevent spoilage of the beer at high temperatures, the shrinkage ratio must be higher even at low temperatures. However, conventional polyester heat-shrinkable films are insufficient for a high shrinkage ratio at low temperatures.

**[0008]** Japanese Laid-open Patent Publication Nos. 63-139725, 7-53416, 7-53737, 7-216107, 7-216109 and 9-254257 taught that the shrinkage rate can be adjusted by blending polyethylene terephthalate or polybutylene terephthalate in a predetermined ratio, or by copolymerizing a dicarbonic component such as a terephthalic acid and an isophthalic acid, and a diol component such as ethylene glycol and 1,4-cyclohexanedimethanol, thereby improving uniformity in shrinkage. Although the suggested methods showed an improvement in terms of uniformity in shrinkage, a shrinkage ratio in the major shrinkage direction is insufficient for use as a full covering for a container. Furthermore, because the shrinkage ratio in a direction perpendicular to the major shrinkage direction is so high, a bowing phenomenon at the edges becomes more serious when it is applied to a rectangular container, thereby deteriorating the appearance of the label with poor transparency.

**[0009]** To improve the edge bowing phenomenon, Japanese Laid-open Patent Publication Nos. 9-239834 and 10-77335 suggested that the shrinkage ratio be adjusted using a polyester copolymer such as neopentylglycol[2,2-dimethyl(-1,3-propane diol, or by performing a post-drawing process accompanied with a thermal treatment. However, the shrinkage stress in a direction perpendicular to the major shrinkage direction is too high to overcome the edge bowing phenomenon by the suggested method, and the thermal shrinkage ratio in the major shrinkage direction is insufficient to be used as a full covering for a container. As illustrated in FIG. 2, another drawback is that a shrinkable film 21 cannot accurately fit to the shape of a glass bottle 20 near a cap 22, thereby resulting in poor appearance and incomplete sealing. Thus, it is very likely that external contaminants enter the glass bottle 20, causing spoilage of the content.

**[0010]** To solve the above problems, it is a objective of the present invention to provide a heat-shrinkable polyester film for use as labels or coverings for a variety of containers, which shows an excellent shrinkage property in addition to having superior transparency, printability, film-to-flux adhesiveness and ease of drawing process.

**[0011]** It is another object of the present invention to provide a method for manufacturing the heat-shrinkable poly-

ester.

[0012] The first objective of the present invention is achieved by a heat-shrinkable polyester film comprising: a repeating unit of trimethyleneterephthalate of 5 - 30% by mole; a repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate of 5 - 30% by mole of the total composition; and a repeating unit of ethyleneterephthalate for the balance.

[0013] Preferably, to make the film opaque, the heat-shrinkable polyester film further comprises a white inorganic pigment of 5 - 25% by weight of the film.

[0014] The second objective of the present invention is achieved by a method for manufacturing the thermal shrinkable polyester film including a repeating unit of trimethyleneterephthalate of 5 - 30% by mole; a repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate of 5 - 30% by mole of the total composition, and a repeating unit of ethyleneterephthalate for the balance, the method comprising blending polyethyleneterephthalate, polytrimethyleneterephthalate, and 2,2-dimethyl(-1,3-propane)diol polyester copolymerized from a dicarbonic acid component and diol components to obtain a polyester series resin mixture, wherein the dicarbonic component is terephthalic acid or dimethylterephthalate, and the diol components are ethylene glycol and 2,2-dimethyl(-1,3-propane)diol. Next, the polyester series resin mixture is extruded and molded to prepare a molten sheet. The molten sheet is cooled and solidified to prepare a solidified sheet, and then drawn.


[0015] Preferably, in the manufacture of the heat-shrinkable polyester film according to the present invention, a repeating unit of ethyleneterephthalate is comprised of 70 - 93% by mole of the 2,2-dimethyl(-1,3-propane)diol polyester copolymer and a repeating unit of dimethyl(-1,3-propylene)terephthalate is comprised of 7 - 30% by mole of the 2,2-dimethyl(-1,3-propane)diol polyester copolymer.

[0016] The above objectives and advantages of the present invention will become more apparent by describing in detail preferred embodiments thereof with reference to the attached drawings in which:

FIG. 1 shows a bowing phenomenon at an edge of a heat-shrinkable film used as a label for a rectangular container according to the prior art; and

FIG. 2 is a sectional view of a glass bottle fully covered with a heat-shrinkable film, according to the present invention.

[0017] A heat-shrinkable polyester film according to the present invention comprises a repeating unit of trimethyleneterephthalate having formula (1) below in an amount of 5 to 30%, and a repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate having formula (2) below in an amount of 5 to 30% of the total composition by mole, and ethyleneterephthalate having formula (3) for the balance.



[0018] In formulae (1) through (3),  $n$  is a positive integer.

[0019] Thermal shrinkage properties of polyester films originate from their amorphous molecular chain. As for the polyester film according to the present invention, the repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate contributes to enhancing the amorphous property, thereby resulting in sufficient thermal shrinking to be used as a film. In addition, the repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate has a branched molecular structure, which improves the mechanical properties of a single-direction drawn polyester film in both the drawing direction and in a direction perpendicular to the drawing direction. As a result, film splitting which is commonly shown in a single-direction drawn polyester film can be prevented, and thus single directional drawing with a high drawing ratio can be achieved. On the other hand, the repeating unit of trimethyleneterephthalate enhances the surface adhesiveness of the film, printability, and drawing properties in the manufacture of the film.

[0020] To give more attractive properties to the polyester film, each of the repeating units of 2,2-dimethyl(-1,3-propylene)terephthalate and trimethyleneterephthalate is contained in an amount of 5 to 30% of the total composition by mole. If the content of each of the repeating units is less than 5% by mole, the previously mentioned film properties may be unsatisfactory. On the other hand, if the content of each of the repeating units exceeds 30% by mole, the content of the repeating unit of ethyleneterephthalate, which is relatively cheaper, can be reduced, thereby increasing the manufacturing cost of film. Furthermore, the mechanical properties and heat resistance of the film are deteriorated.


[0021] In the present invention, components other than the above-listed components can be further incorporated into the film to the extent that the thermal shrinkage properties are not influenced by addition of other components. For example, terephthalate components can be replaced by isophthalate components. Also, polyvalent carbonic acid as an acid component, including isophthalic acid or an ester thereof, 2,6-naphthalenedicarboxylic acid or an ester thereof, sebacic acid, adipic acid, 5-sodiumsulfurisophthalic acid, trimellitic acid, oxalic acid, malonic acid, succinic acid, glutaric acid, pimelic acid, azelaic acid, pyromellitic acid, and a polyhydric alcohol as a diol component, including diethyleneglycol, hexanediol, diol of 2,2(4-oxyphenol)propane derivatives, xylene glycol, 1,4-cyclohexane dimethanol, triethylene glycol and polytetramethylene glycol can be further added.

[0022] To provide the polyester film with opaqueness, the heat-shrinkable polyester film according to the present invention may further comprise a white inorganic pigment in an amount of 5 to 25% by weight of the film. In this case, it is preferable that the content of the repeating unit of trimethyleneterephthalate is in the range of 10 to 30% by mole, and the content of the repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate is in the range of 5 to 20% by mole. If the content of the white inorganic pigment is less than 5% by weight, the whiteness and opaqueness of the film are poor. Meanwhile, if the content of the white inorganic pigment is more than 25% by weight, the mechanical properties of the polyester film can be deteriorated, so that a successful drawing process cannot be ensured. As a result, it is difficult to produce a film with a uniform thickness. More preferably, the white inorganic pigment is at least one selected from the group consisting of titanium oxide, barium sulfide and calcium carbonate.

[0023] In the case where a white inorganic pigment is added in the manufacture of the heat-shrinkable polyester film according to the present invention, preferably, the heat-shrinkable polyester film has a whiteness of 80% or more based on ASTM E313, a transmittance of 40% or less at a thickness of 40 $\mu$ m based on ASTM D1003, a surface adhesiveness of 5B grade or higher with respect to nitrocellulose series ink, a shrinkage ratio of 40% or more in the major shrinkage direction in 80°C-water, and a shrinkage ratio of 5% or less in a direction perpendicular to the major shrinkage direction. The white and opaque polyester film has superior printability due to its excellent adhesiveness with respect to ink, and thus good appearance can be provided to the film by application of a simple printing process which uses 1 to 3 colors, without need for a complicated gravure printing process which uses 5 or more colors. Since the shrinkage ratio in the major shrinkage direction is as high as 40% or more and that in a direction perpendicular to the major shrinkage is small, the bowing phenomenon at edges of film is minimized.

[0024] According to another aspect of the present invention, a method for manufacturing the heat-shrinkable polyester film including the repeating unit of trimethyleneterephthalate in an amount of 5 to 30%, the repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate in an amount of 5 to 30% of the total composition by mole, and ethyleneterephthalate for the balance involves: blending polyethyleneterephthalate, polytrimethyleneterephthalate, and 2,2-dimethyl(-1,3-propane)diol polyester copolymerized from a dicarbonic acid component and diol components to obtain a polyester series resin mixture, wherein the dicarbonic acid component is terephthalic acid or dimethylterephthalate, and the diol components are ethylene glycol and 2,2-dimethyl(-1,3-propane)diol; extruding and molding the polyester series resin mixture to prepare a molten sheet; cooling and solidifying the molten sheet to prepare a solidified sheet; and drawing the solidified sheet.

[0025] To incorporate the above amount of the repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate into the heat-shrinkable polyester film according to the present invention, it is preferable to blend 2,2-dimethyl(-1,3-propane)diol polyester copolymer having formula (4). 2,2-dimethyl(-1,3-propane)diol polyester copolymer is obtained by copolymerizing terephthalic acid or dimethylterephthalate, which is a dicarbonic acid, and ethylene glycol and 2,2-dimethyl(-1,3-propane)diol, which are diol components.



[0026] In formula (4), n and m are positive integers.

[0027] Preferably, 2,2-dimethyl(-1,3-propane)diol polyester copolymer has a limiting viscosity of 0.5 to 0.8, and includes the repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate in an amount of 5 to 30% by mole. If the content of the repeating unit is less than 7% by mole, the heat shrinkage properties of the film are unsatisfactory. If the content of the repeating unit is more than 30% by mole, increasing the degree of polymerization up to such a level may be difficult, and the high degree of copolymerization makes the film excessively amorphous. As a result, it is impossible to perform pre-crystallization which is needed so as to prevent melting and agglomerating during a drying process, and thus the drying process must be carried out at a low temperature for a long period of time. In addition, a melting extruder exclusively used for amorphous polymers must be devised.

[0028] In the manufacture of the heat-shrinkable polyester film according to the present invention, it is preferable to use polyethylene terephthalate having a limiting viscosity of 0.5 to 0.8 and polytrimethyleneterephthalate having a limiting viscosity of 0.6 to 1.0.

[0029] On the other hand, copolymerizing both of the dicarbonic acids, terephthalic acid and dimethylterephthalate, and three diol components including ethylene glycol, 1,3-propane diol and 2,2-dimethyl(-1,3-propane) diol hinders the full exhibition of the intrinsic properties of the repeating units of trimethyleneterephthalate and dimethyl(-1,3-propylene)terephthalate, which is not preferable. In this case, the thermal shrinkage properties of the film are unsatisfactory, the degree of copolymerization is too high, and the film is too amorphous. Thus, pre-crystallization, which is necessary to prevent melting and agglomerating during a drying process, is not able to be performed. As a result, the film must be dried at low temperatures for a long period of time. Furthermore, a melting extruder must be devised for amorphous polymers.

[0030] A variety of polyesters that constitute the heat-shrinkable polyester film can be synthesized by a well-known method, such as direct esterification or interesterification.

[0031] A composition for the heat-shrinkable polyester film according to the present invention may include a variety of additives. For example, to improve slipperiness of the film during a manufacturing process, a spherical silica, gel-type silica, alumina, caoline or calcium carbonate may be added in the preparation of the polymers previously mentioned. In addition, titanium dioxide or barium sulfate particles may be added in a predetermined amount to give a unique appearance or opaqueness to a label.

[0032] The method for manufacturing the heat-shrinkable polyester film according to the present invention involves extruding and molding a mixture of 1,3-propane diol polyester copolymer and dimethyl(-1,3-propylene)terephthalate polyester copolymer; cooling and solidifying the molded product; and single-direction or bidirection drawing the solidified product. A thermal fixation process may be further performed as needed. The heat-shrinkable polyester film manufacturing method will be described in greater detail.

[0033] Firstly, 1,3-propane diol polyester copolymer and dimethyl(-1,3-propylene)terephthalate polyester copolymer are mixed well, and the mixture is melted and extruded into a molten sheet. As for the extruding and molding process using an extruder, the mixture is usually melted by heating. In certain cases, resins may be softened, rather than be melted, and then molded. The extruder may be a single-screw extruder, twin-screw and single-directional extruder, or twin-screw and bidirectional extruder. For uniform physical properties, it is preferable to use a single-screw serial random type extruder, which shows excellent mixing capability. The mixture is mixed and melted in the extruder and extruded through a die, resulting in a molten sheet. The die may be a T-die or an annular die.

[0034] The molten sheet extruded from the die is rapidly cooled to obtain a solidified sheet. Such cooling and solidification may be performed by a metal roller with a gaseous or liquid coolant. Use of metal roller improves the surface properties of the sheet with uniform thickness. Preferably, the cooling and solidification is performed in a state where the sheet is less oriented.

[0035] The solidified sheet is simultaneously or sequentially drawn with a single screw. Sequential drawing is more preferable to enhance the uniformity in thickness.

[0036] In the preferred embodiment of the present invention, the film drawn in a longitudinal direction may be further drawn in the traverse direction, i.e., perpendicular to the traveling direction of the film as needed. Any drawing method

which is well known to one skilled in the art may be applicable. A traverse drawing method using a tenter, which is the most typical drawing method, is preferred. According to the traverse drawing method, two opposite sides of the film are fixed to a pair of clips, which are separated from each other by a predetermined distance, and continuously travels. The temperature of atmosphere is properly adjusted, and the distance between the two clips is widened to draw the film.

**[0037]** The heat-shrinkable polyester film according to the present invention has excellent drawing properties, and thus the drawing method using a tenter is applicable to the heat-shrinkable polyester film with uniform drawing properties, thereby resulting in a film with uniform thickness. Thus, when the heat-shrinkable polyester film is used as a wrapping material or a label for a variety of containers, its uniform shrinkage property gives it an attractive appearance.

**[0038]** Besides the drawing method using a tenter, various other methods including a gas pressure method and a milling method, or a combination of these methods are applicable.

**[0039]** To adjust the thermal shrinkage ratio of the film, which has passed through the drawing process, a thermal fixation process may be performed as needed. For example, the thermal fixation may be performed at 80 to 100°C for 10 to 300 seconds while the drawn film is fully extended, relaxed, or shrunk to a certain extent. The optimum temperature for the fixation varies depending on the speed of the film passing through a thermal processing unit, i.e., depending on time period of the thermal fixation.

**[0040]** The present invention will be described in greater detail by means of the following examples. The following examples are for illustrative purposes and not intended to limit the scope of the invention.

#### Synthesis Example 1

**[0041]** Polyethyleneterephthalate (A1) having a limiting viscosity of 0.62 was synthesized by a common method.

**[0042]** 100 parts by mole of dimethylterephthalate and 140 parts by mole of 1,3-propane diol were put into an autoclave equipped with a mixer and a distillation column, and tetrabutylenetitanate as a catalyst for interesterification was added in an amount of 0.05% by weight of dimethylterephthalate. After removing methanol, which was a byproduct, the temperature was raised up to 220°C for further reaction. After the interesterification was completed, trimethylphosphate as a stabilizer was added in an amount of 0.045% by weight of dimethylterephthalate, and antimonytrioxide as a polymerization catalyst was further added 10 minutes later in an amount of 0.02% by weight. After 5 minutes, the resulting product was transferred into a second reactor equipped with a vacuum unit, and reacted at 280°C for about 180 minutes for polymerization, so that a polymer (B1) of trimethyleneterephthalate having a limiting viscosity of 0.85 was obtained.

**[0043]** 100 parts by mole of dimethylterephthalate, 110 parts by mole of ethyleneglycol and 40 parts by mole of neopentylglycol (2,2-dimethyl(-1,3-propane)diol) were put into an autoclave equipped with a mixer and a distillation column, and manganese acetate as a catalyst for interesterification was added in an amount of 0.07% by weight of dimethylterephthalate. After removing methanol, which was a byproduct, the temperature was raised up to 220°C for further reaction. After the interesterification was completed, trimethylphosphate as a stabilizer was added in an amount of 0.04% by weight of dimethylterephthalate. After 5 minutes, antimonytrioxide in an amount of 0.035% by weight, as a catalyst for polymerization, and 0.005% by weight of the tetrabutylenetitanate were added, and stirred for 10 minutes. Next, the resulting product was transferred into a second reactor equipped with a vacuum unit, and the pressure was slowly reduced while the temperature was raised up to 285°C. The temperature was maintained for about 210 minutes for polymerization, thereby resulting in a neopentylglycol polyester copolymer (C1) having a limiting viscosity of 0.60.

#### Examples 1 through 6, and Comparative Examples 1 through 6

**[0044]** To avoid melting during a drying process, polyethyleneterephthalate (A1), trimethyleneterephthalate (B1) and neopentylglycol polyester copolymer (C1), which, which were prepared in Synthesis Example 1, were pre-crystallized, and then mixed in various ratios listed in Table 1. Each of the mixtures was dried in a rotary vacuum drier until the moisture content reached 0.005% or less by weight. The content of the repeating units of ethyleneterephthalate (A'), trimethyleneterephthalate (B') and dimethyl(-1,3-propylene)terephthalate (C') for the dried polyester mixtures for each sample was analyzed. The results are shown in Table 2.

**[0045]** Each of the polyester mixtures was melted at 280°C, extruded, and cooled by a casting roller whose temperature was maintained at 20°C, thereby resulting in an amorphous sheet. The amorphous sheet was sequentially drawn to 3.6 times its original length by a tenter at 80°C, so that a single-direction drawn heat-shrinkable polyester film having a thickness of 50 μm was obtained.

Table 1

Example	Composition of Film				
	Polymer A1 (% by weight)	Polymer B2 (% by weight)	Copolymer C1		
Copolymerization ratio (% by mole)	(% by weight)				
			EG*	NPG	
Example 1	0	50	42	58	50
Example 2	10	50	42	58	40
Example 3	15	35	49	51	50
Example 4	0	25	82	18	75
Example 5	30	15	82	18	55
Example 6	75	10	82	18	25
Comparative Example 1	85	3	82	18	12
Comparative Example 2	0	0	81	19	100
Comparative Example 3	75	25	0	0	0
Comparative Example 4	65	35	82	18	10
Comparative Example 5	58	7	82	18	35

\* EG and NPG are abbreviations for ethyleneglycol and neopentylglycol, respectively.

Table 2

Example	Content of Repeating Units (% by mole)		
	A'	B'	C'
Example 1	51	25	24
Example 2	61	25	14
Example 3	66	20	14
Example 4	75	14	11
Example 5	82	10	8
Example 6	88	5	7
Comparative Example 1	95	3	2
Comparative Example 2	81	0	19
Comparative Example 3	79	21	0
Comparative Example 4	72	25	3
Comparative Example 5	83	2	15

#### Synthesis Example 2

[0046] 100 parts by mole of dimethylterephthalate and 180 parts by mole of ethyleneglycol were put into an auto-

clave equipped with a distillation column, and manganese acetate as a catalyst for interesterification at 150°C was added in an amount of 0.05% by weight of dimethylterephthalate. After removing methanol, which was a byproduct, the temperature was raised up to 220°C for further reaction. After the interesterification was completed, trimethylphosphate as a stabilizer was added in an amount of 0.045% by weight of dimethylterephthalate. After 10 minutes, antimonytrioxide of 0.03% by weight, as a catalyst for polymerization, was added. After 5 minutes, the resulting product was transferred into a second reactor equipped with a vacuum unit, and maintained at 280°C for about 140 minutes for polymerization, so that a polymer (A2) of polyethyleneterephthalate having a limiting viscosity of 0.62 was obtained.

**[0047]** Polymerization was carried out in the same way as for the polymer (A2) of polyethyleneterephthalate, except that trimethyleneglycol as a diol component was used instead of ethyleneglycol, so that a polymer (B2) of polytrimethyleneterephthalate having a limiting viscosity of 0.85 was obtained.

**[0048]** Polymerization was carried out in the same way as for the polymer (A2) of polyethyleneterephthalate, except that 180 parts by mole of ethyleneglycol added as a diol component was replaced by 90 parts by mole of ethyleneglycol and 90 parts by mole of 2,2-dimethyl(-1,3-propane)diol, so that 2,2-dimethyl(-1,3-propane)diol polyester copolymer (C2), which had a limiting viscosity of 0.64, was obtained.

**[0049]** The obtained polymer (A2) of polyethyleneterephthalate and titanium oxide (having an average particle size of 0.5 µm) having the same crystalline structure as that of anatase were mixed in a ratio of 1:1 by weight to manufacture a titanium oxide master chip (D2).

#### Examples 7 through 19, and Comparative Examples 6 and 7

**[0050]** The polymer (A2) of polyethyleneterephthalate, the polymer (B2) of polytrimethyleneterephthalate, the polyester copolymer (C2) including 2,2-dimethyl(-1,3-propane)diol, and the titanium oxide master chip (D2), which were prepared in Synthesis Example 2, were separately dried until the moisture content reached 0.05% or less by weight. The dried polymers were mixed in various ratios shown in Table 3. The content of the repeating units of ethyleneterephthalate (A"), trimethyleneterephthalate (B") and dimethyl(-1,3-propylene)terephthalate (C") for the dried polyester mixtures for each sample was analyzed. The results are shown in Table 4.

**[0051]** Each of the polyester mixtures was melted at 280°C, extruded, and cooled by a casting roller whose temperature was maintained at 30°C, thereby resulting in an amorphous sheet. The amorphous sheet was sequentially drawn to 3.5 times its original length by a tenter, so that a single-direction drawn heat-shrinkable polyester film having a thickness of 40 µm was obtained.



Table 3

Example	Composition of Film					
	A2 (% by weight)	B2 (% by weight)	C2			D2 (% by weight)
Copolymerization Ratio (% by mole)	(% by weight)					
			EG*	DMPG		
Example 7	34	20	50	50	32	28
Example 8	39	15	50	50	32	28
Example 9	29	25	50	50	32	28
Example 10	30	20	50	50	36	28
Example 11	42	20	50	50	24	28
Example 12	25	25	50	50	36	28
Example 13	47	15	50	50	24	28
Example 14	40	20	50	50	32	16
Example 15	26	20	50	50	32	44
Example 16	49	5	50	50	32	28
Comparative Example 6	14	40	50	50	32	28
Comparative Example 7	60	20	50	50	6	28
Example 17	16	20	50	50	50	28
Example 18	46	20	50	50	32	4
Example 19	8	20	50	50	32	80

\* EG and DMPG are abbreviations for ethyleneglycol and 2,2-dimethyl(-1,3-propane)diol, respectively.

Table 4

Example	Content of Repeating Units (% by mole)			TiO <sub>2</sub> (% by weight)*
	A"	B"	C"	
Example 7	64	20	16	12.3
Example 8	69	15	16	12.3
Example 9	59	25	16	12.3
Example 10	62	20	18	12.3
Example 11	68	20	12	12.3
Example 12	57	25	18	12.3
Example 13	73	15	12	12.3
Example 14	64	20	16	7.4
Example 15	64	20	16	18
Example 16	79	5	16	12.3
Comparative Example 6	44	40	16	12.3
Comparative Example 7	77	20	3	12.3
Example 17	55	20	25	12.3
Example 18	64	20	16	2
Example 19	64	20	16	28.6

\* The content of TiO<sub>2</sub> is based on the weight of film.

**[0052]** The performances of the polyester films manufactured in the examples and the comparative examples were measured in terms of the following properties. The results are shown in Tables 5 and 6.

#### (1) Thermal shrinkage ratio

**[0053]** A polyester film was cut into pieces of 15mm (width) by 200mm (length). The cut polyester film was put in water whose temperature was kept at 80°C. The length of the piece was measured before and after the thermal treatment, and the thermal shrinkage ratio was evaluated by the following formula

$$\text{Thermal shrinkage ratio (\%)} = [(L - \ell) / L] \times 100$$

where L is the length of film before thermal treatment, and  $\ell$  is the length of film after thermal treatment.

#### (2) Printability

**[0054]** Nitrocellulose series ink was spread over the surface of the film and patterned regularly with a predetermined interval using a razor blade. A semitransparent tape having an adhesive strength of 40 g/mm was adhered to the ink-coated surface of the film with the application of pressure. The printability was evaluated by the amount of ink transferred onto the tape when the tape adhered to the ink-coated surface was separated from the surface, according to the following criteria.

○ : No ink was transferred onto the tape.

△ : 70% or less of the ink was transferred onto the tape.

X : 70% or more of the ink was transferred onto the tape.

## (3) Adhesive property with respect to flux

**[0055]** The adhesiveness of the films with respect to tetrahydrofuran (THF), which is a common flux, was evaluated according to the following criteria.

- : A film-and-flux contact portion was transparent and instantaneous adhesiveness was excellent.  
 X : The adhesiveness of the film was almost zero and instantaneous adhesiveness was poor

## (4) Coating property over glass bottle

**[0056]** Grids each having a size of 10 mm by 10 mm were patterned over the manufactured heat-shrinkable films, and then rolled and adhered with THF into a cylindrical shape having a diameter of 65 mm. Then, a commercially available glass bottle (having a capacity of 334 ml) was covered with the cylindrical heat-shrinkable film in water whose temperature was kept at 85°C or 90°C. Next, the coating property was evaluated according to the following criteria.

- : Grids were uniform over the glass bottle and the accuracy with which the film fitted to the shape of the lid of the bottle was good after covering at 90°C.  
 △ : Grids are uniform over the glass bottle and the accuracy with which the film fitted to the shape of the lid of the bottle was good after covering at 85°C.  
 X : Grids are nonuniform over the glass bottle and the accuracy with which the film fitted to the shape of the lid of the bottle was poor after covering at 85°C.

## (5) Bowing phenomenon

**[0057]** A rectangular PET bottle having a side width of 8 cm was covered with the manufactured heat shrinkable film having a width 10 cm in 80°C-water for 10 seconds. Next, the degree to which the edge of the film bowed inward was measured.

## (6) Extendability

**[0058]** The appearance and the uniformity in thickness of the film after having been drawn were observed, and evaluated according to the following criteria.

- : Film had good uniformity in thickness without being whitened.  
 X : Either film became whitened or had nonuniformity in thickness.  
 ∅ : Evaluation of the extendability of film was impossible due to so irregular extensibility of film.

## (7) Rupture strength

**[0059]** The rupture strength of the manufactured films was measured using a tensile strength tester (Model 6021, manufactured by Instron Co.). For measuring the rupture strength, the films were cut into pieces (10cm-length by 15mm-width), and the rupture strength was measured at room temperature.

## (8) Haze

**[0060]** The haze of the manufactured films was measured using a haze tester (Model xl-211, manufactured by Gardner Neotech.)

## (9) Whiteness

**[0061]** The whiteness of the manufactured films was measured according to ASTM E313-96.

## (10) Light Transmittance

**[0062]** The light transmittance of the manufactured film was measured according to ASTM D1003 (with a 25mm-diameter at 2.5°-angle of scattering).

## (11) Adhesiveness with respect to nitrocellulose ink

[0063] The adhesiveness of the films with respect to nitrocellulose ink was measured according to ASTM D3359-83.

## (12) Spontaneous Shrinkage Ratio

[0064] The manufactured films were cut into pieces having a width of 15 mm and a length of 200 mm, and left for 7 days in an oven whose temperature was set at 40°C. The length of the film was measured before and after putting the film into the oven, and the spontaneous shrinkage ratio was calculated by the same formula used to calculate the thermal shrinkage ratio.

## (13) Appearance

[0065] The appearance of the manufactured films was visually inspected according to the following criteria, after having been shrunk by 30% in 80°C-water in the traverse direction with respect to the major shrinkage direction.

⊙ : excellent appearance (no wrinkles and no cloudiness)

X : poor appearance (with both wrinkles and cloudiness)

Table 5

Example	Shrinkage Ratio in 80°C water (%)		Extensibility of film	Tensile strength in major shrinkage direction (kg/mm <sup>2</sup> )	Haze (%)	Bowing phenomenon	Coating property	Printability	Adhesiveness with respect to flux
	MD*	TD							
Example 1	61	-1.9	⊙	6.8	3.9	0	Δ	Δ	⊙
Example 2	69	-1.0	⊙	5.7	3.9	0	⊙	⊙	⊙
Example 3	72	0	⊙	5.5	4.2	0	⊙	⊙	⊙
Example 4	71	0	⊙	5.2	4.7	0.4	⊙	⊙	⊙
Example 5	72	0.8	⊙	5.4	5.2	0.9	⊙	⊙	⊙
Example 6	65	1.1	⊙	4.9	5.3	1.2	X	⊙	⊙
Comparative Example 1	61	3.9	X	6.2	7.8	3.1	X	Δ	X
Comparative Example 2	-	-	⊙	-	-	-	-	-	-
Comparative Example 3	41	9.4	⊙	immeasurable	5.1	6.7	X	Δ	X
Comparative Example 4	64	3.7	X	immeasurable	4.9	-	Δ	Δ	X
Comparative Example 5	55	4.3	X	5.3	10.2	3.5	X	X	X

\* MD and TD indicate the shrinkage ratios in the major shrinkage direction and in the traverse direction with respect to the major shrinkage direction, respectively, of the films.

[0066] As shown in FIG. 5, the heat-shrinkable polyester films manufactured in Examples 1 through 6 according to the present invention are superior in terms of

[0067] As shown in FIG. 5, the heat-shrinkable polyester films manufactured in Examples 1 through 6 according to the present invention are superior in terms of extendability, tensile strength, film-and-flux adhesiveness, transparency, printability and thermal shrinkage ratio in the major shrinkage direction, and the bowing phenomenon at edge of the film was almost non-existent. Thus, the heat-shrinkable films having such excellent properties can be used as labels or coverings for a variety of containers.

[0068] As for the heat-shrinkable polyester films according to the present invention, it is concluded that if the content of the repeating unit of trimethylene terephthalate is less than 5 mole% (Comparative Examples 1, 2 and 5), the shrinkage ratio in the traverse direction with respect to the major shrinkage direction increases, so that the bowing phenomenon is shown at the edge of the film. Furthermore, the film-and-flux adhesiveness and the transparency of the film are degraded. On the other hand, if the content of the repeating unit of dimethyl(-1,2-propylene)terephthalate is less than 5 mole%, the tensile strength of the film in the major shrinkage direction sharply decreases.

Table 6

Example	Properties of Polyester Films								Appearance
	White- ness (%)	Light Transmi- tance (%)	Adhesiv- ness with respect to NC ink** (grade)	Rupture Strength (kgf/mm <sub>2</sub> )		Spontane- ous shrinkag e ratio (%)	Thermal Shrinkage Ratio (%)		
				MD*	TD	TD	MD	TD	
Example 7	105	21	5B	6.9	22.1	0.2	3	62	⊙
Example 8	105	21	5B	6.9	22.5	0.2	3	55	⊙
Example 9	105	21	5B	6.9	21.2	0.2	3	66	⊙
Example 10	105	21	5B	7.4	21.9	0.3	3	70	⊙
Example 11	105	21	5B	5.9	22.4	0.2	4	54	⊙
Example 12	105	21	5B	7.3	20.7	0.4	4	71	⊙
Example 13	105	21	5B	6.1	22.8	0.2	4	50	⊙
Example 14	95	30	5B	7.1	22.3	0.2	3	64	⊙
Example 15	112	15	5B	6.2	20.5	0.2	3	58	⊙
Example 16	105	21	5B	6.9	22.2	0.2	3	57	X
Comparative Example 6	105	21	5B	6.9	16.5	0.5	4	60	⊙
Comparative Example 7	105	21	5B	3.5	22.3	0.2	7	32	⊙
Example 17	105	21	5B	7.8	14.7	0.4	4	68	⊙
Example 18	60	72	5B	6.9	22.2	0.2	3	62	⊙
Example 19	115	11	5B	3.2	13	1.5	7	30	X

\* MD and TD indicate the shrinkage ratios in the major shrinkage direction (lateral direction) and in the traverse direction (longitudinal direction) with respect to the major shrinkage direction, respectively, of the films.

\*\* NC ink indicates nitrocellulose series ink.

[0069] Referring to Table 6, as for the heat-shrinkable polyester films of Examples 7 through 15, which contain white pigment, all properties including whiteness, light transmission, adhesiveness with respect to ink, mechanical properties, shrinkage properties and appearance are excellent. In addition, if the content of titanium oxide is less than 5% by weight of the film (Example 18), the heat shrinkage property is good, but the whiteness and opaqueness of the

film is less satisfactory than desired. Meanwhile, if the content of titanium oxide is more than 25% by weight, the thermal shrinkage property deteriorates thus giving a poor appearance.

[0070] When the content of the repeating unit of trimethylene terephthalate exceeds 30 mole%, the rupture strength of film decreases (Comparative Example 6). When the content of the repeating unit of dimethyl(-1,3-propylene)terephthalate is less than 5 mole% (Comparative Example 7), the thermal shrinkage properties of the film sharply deteriorate.

[0071] As previously described, the heat-shrinkable polyester films according to the present invention satisfy the need for excellent basic properties including transparency, printability, film-and-flux adhesiveness and ease of drawing process, and thus they can be applicable as labels or coverings for a variety of containers. In particular, when the heat-shrinkable polyester films according to the present invention are used as a label for a rectangular container, the bowing of the film at the edge in the traverse direction with respect to a major shrinkage direction can be minimized. Furthermore, addition of inorganic pigments and metal sulfonate derivative can give whiteness, opaqueness and static-eliminating properties to the heat-shrinkable polyester films according to the present invention.

## Claims

1. A heat-shrinkable polyester film comprising;

a repeating unit of trimethyleneterephthalate of 5 - 30% by mole;

a repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate of 5 - 30% by mole of the total composition; and  
a repeating unit of ethyleneterephthalate for the balance.

2. The heat-shrinkable polyester film according to claim 1, further comprising a white inorganic pigment in an amount of 5 - 25% by weight of the film.

3. The heat-shrinkable polyester film according to claim 2, wherein the white inorganic pigment is at least one selected from titanium oxide, barium sulfide and calcium carbonate.

4. The heat-shrinkable polyester film according to any of claims 1 to 3, wherein the content of the repeating unit of trimethyleneterephthalate is in the range of 10 - 30% by mole, and the content of the repeating unit of 2,2-dimethyl(-1,3-propylene)terephthalate is in the range of 5 - 20% by mole.

5. The heat-shrinkable polyester film according to any of claims 2 to 4, wherein the polyester film has a whiteness of 80% or more based on ASTM E313, a light transmittance of 40% or less at a thickness of 40  $\mu$ m based on ASTM D1003, a surface adhesiveness of 5B grade or more with respect to nitrocellulose series ink based on ASTM D3359, a shrinkage ratio of 40% or more in the major shrinkage direction in 80°C-water, and a shrinkage ratio of 5% or less in the traverse direction with respect to the major shrinkage direction.

6. A method for manufacturing the heat-shrinkable polyester film of claim 1, comprising:

blending polyethyleneterephthalate, polytrimethyleneterephthalate, and 2,2-dimethyl(-1,3-propane)diol polyester copolymerized from a dicarbonic acid component and dial components to obtain a polyester series resin mixture, wherein the dicarbonic component is terephthalic acid or dimethylterephthalate, and the diol components are ethylene glycol and 2,2-dimethyl(-1,3-propane)diol;

extruding and molding the polyester series resin mixture to prepare a molten sheet;

cooling and solidifying the molten sheet to prepare a solidified sheet; and  
drawing the solidified sheet.

7. The method according to claim 6, wherein the polytrimethyleneterephthalate has a limiting viscosity of 0.6 - 1.0.

8. The method according to claim 6 or 7, wherein the 2,2-dimethyl(-1,3-propane)diol polyester copolymer has a limiting viscosity of 0.5 to 0.8.

9. The method of according to any of claims 6 to 8, wherein a repeating unit of ethyleneterephthalate is comprised of 70 - 93% by mole of the 2,2-dimethyl(-1,3-propane)diol polyester copolymer and a repeating unit of dimethyl(-1,3-propylene)terephthalate is comprised of 7 - 30% by mole of the 2,2-dimethyl(-1,3-propane)diol polyester copolymer.

FIG. 1 (PRIOR ART)






FIG. 2





Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 072 632 A3**

(12)

## EUROPEAN PATENT APPLICATION

(88) Date of publication A3:  
13.06.2001 Bulletin 2001/24

(51) Int Cl.7: **C08J 5/18**, C08L 67/02,  
C08G 63/183

(43) Date of publication A2:  
31.01.2001 Bulletin 2001/05

(21) Application number: **00306214.8**

(22) Date of filing: **21.07.2000**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **27.07.1999 KR 9930554**  
**08.10.1999 KR 9943482**

(71) Applicant: **SKC Co., Ltd.**  
**Suwon-city, Kyungki-do (KR)**

(72) Inventors:  
• **Kim, Nam-il**  
**Jangan-gu Suwon City, Kyungki-do (KR)**  
• **Kim, Sang-il**  
**Kwonsun-gu Suwon-City, Kyungki-do (KR)**

(74) Representative: **Kyle, Diana**  
**Elkington and Fife**  
**Prospect House**  
**8 Pembroke Road**  
**Sevenoaks, Kent TN13 1XR (GB)**

(54) **Heat-shrinkable polyester film and method for manufacturing the same**

(57) A heat-shrinkable polyester film including: a repeating unit of trimethyleneterephthalate of 5 - 30% by mole; a repeating unit of 2,2-dimethyl(-1,3-propylene) terephthalate of 5 - 30% by mole of the total composition; and a repeating unit of ethyleneterephthalate for the bal-

ance. The heat-shrinkable polyester film has excellent printability, mechanical properties, film-and-flux adhesiveness and shrinkage properties, and ease of drawing process. Thus, the heat-shrinkable polyester film can be used as labels or coverings for a variety of containers.

**EP 1 072 632 A3**





European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 00 30 6214

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (InLCI.7)
Y	PATENT ABSTRACTS OF JAPAN vol. 15, no. 227 (C-0839), 10 June 1991 (1991-06-10) & JP 03 068635 A (MITSUBISHI RAYON CO LTD), 25 March 1991 (1991-03-25) * abstract * & DATABASE WPI Week 199118 Derwent Publications Ltd., London, GB; AN 1991-129173 * abstract *	1-5	C08J5/18 C08L67/02 C08G63/183
Y	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 11, 26 December 1995 (1995-12-26) & JP 07 216107 A (TOYOSO CO LTD), 15 August 1995 (1995-08-15) * abstract * & DATABASE WPI Week 199541 Derwent Publications Ltd., London, GB; AN 1995-317561 * abstract *	1-5	TECHNICAL FIELDS SEARCHED (InLCI.7)  C08L C08G C08J
Y	US 4 996 291 A (YOSHINAKA ET AL.) 26 February 1991 (1991-02-26) * column 5, line 28 - column 6, line 60 *	1-5	
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>23 April 2001</b>	Examiner <b>Lensen, H</b>
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 (03/02) (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 30 6214

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

23-04-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 03068635 A	25-03-1991	NONE	
JP 07216107 A	15-08-1995	NONE	
US 4996291 A	26-02-1991	JP 1004326 A	09-01-1989
		JP 1981614 C	25-10-1995
		JP 5033895 B	20-05-1993
		JP 1136721 A	30-05-1989
		JP 2062441 C	24-06-1996
		JP 7098357 B	25-10-1995
		JP 1136722 A	30-05-1989
		JP 4079822 B	17-12-1992
		JP 6018902 B	16-03-1994
		JP 63156833 A	29-06-1988
		JP 1997482 C	08-12-1995
		JP 7022966 B	15-03-1995
		JP 63168329 A	12-07-1988
		JP 1160632 A	23-06-1989
		JP 2517995 B	24-07-1996
		DE 3752051 D	22-05-1997
		DE 3752051 T	24-07-1997
		EP 0271928 A	22-06-1988
		EP 0751183 A	02-01-1997
		KR 9207711 B	15-09-1992

EPO FORM P4159

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82